

3rd International Seminar on Chemistry

Innovations and Advances in Chemistry
for the 21st Century Challenges

Procedia Chemistry Volume 17

Bandung, Indonesia
20 - 21 November 2014

Editors:

Hideo Hayashi
Roger Read
Khalijah Awang

ISBN: 978-1-5108-1667-1

Printed from e-media with permission by:

Curran Associates, Inc.
57 Morehouse Lane
Red Hook, NY 12571



Some format issues inherent in the e-media version may also appear in this print version.

Copyright© by Elsevier B.V.
All rights reserved.

Printed by Curran Associates, Inc. (2016)

For permission requests, please contact Elsevier B.V.
at the address below.

Elsevier B.V.
Radarweg 29
Amsterdam 1043 NX
The Netherlands

Phone: +31 20 485 3911
Fax: +31 20 485 2457

<http://www.elsevierpublishingsolutions.com/contact.asp>

Additional copies of this publication are available from:

Curran Associates, Inc.
57 Morehouse Lane
Red Hook, NY 12571 USA
Phone: 845-758-0400
Fax: 845-758-2634
Email: curran@proceedings.com
Web: www.proceedings.com

TABLE OF CONTENTS

THE USE OF DPNR TO PRODUCE TECHNOLOGY PROCESS OF SPONGE FOR FLOATING HOSE	1
<i>Ade Sholeh Hidayat, Ukun M. S. Soedjanaatmadja, Iman Permana Maksum, Iman Rahayu</i>	
COMPUTATIONAL STUDY OF STRUCTURE AND STABILITY OF POLYMERIC COMPLEXES OF $[\text{Fe}_4(\text{HTRZ})_8(\text{TRZ})_4]^{4+}$ AND $[\text{Fe}_4(\text{HTRZ})_{12}]^{8+}$	9
<i>Asep Wahyu Nugraha, Djulia Onggo, Muhamad A. Martoprawiro</i>	
SYNTHESIS OF THE BI-DOPED APATITE-TYPE PHASES $\text{La}_{10-x}\text{Bi}_x\text{Si}_6\text{O}_{27}$ (X= 0.5, AND 1)BY HYDROTHERMAL METHOD	16
<i>Atiek Rostika Noviyanti, Diana Rakhmawaty Eddy, Annisa Anshari</i>	
SYNTHESIS AND CHARACTERIZATION OF HYDROTALCITE AT DIFFERENT MG/AL MOLAR RATIOS	21
<i>Bayu Wiyantoko, Puji Kurniawati, Tri Esti Purbaningtias, Is Fatimah</i>	
SYNTHESIS OF HYDROXYAPATITE FROM RICE FIELDS SNAIL SHELL (BELLAMYA JAVANICA) THROUGH WET METHOD AND PORE MODIFICATION USING CHITOSAN	27
<i>Charlena, Irma Herawati Suparto, Desi Kusuma Putri</i>	
PRELIMINARY INVESTIGATION OF ELECTRICITY PRODUCTION USING DUAL CHAMBER MICROBIAL FUEL CELL (DCMFC) WITH SACCHAROMYCES CEREVISIAE AS BIOCATALYST AND METHYLENE BLUE AS AN ELECTRON MEDIATOR	36
<i>Dani Permana, Desi Rosdianti, Safri Ishmayana, Saadah D. Rachman, Herlian Eriska Putra, Diana Rahayuningwulan, Hari Rom Hariyadi</i>	
THE OLEFIN REACTION BETWEEN CRUDE PALM OIL FATTY ACID METHYL ESTER (CPO FAME) AND ETHYLENE USING GRUBBS II CATALYST	44
<i>Desnelli, D. Mujahidin, Y. Permana, C. L. Radiman</i>	
SYNTHESIS OF FE-TIO₂ COMPOSITE AS A PHOTOCATALYST FOR DEGRADATION OF METHYLENE BLUE	49
<i>Devi Indah Anwar, Dikdik Mulyadi</i>	
SYNTHESIS AND PHOTOCATALYTIC ACTIVITY OF SILICA-BASED SAND QUARTZ AS THE SUPPORTING TIO₂ PHOTOCATALYST	55
<i>Diana Rakhmawaty Eddy, Farisa Novita Puri, Atiek Rostika Noviyanti</i>	
LEACHING AND ADSORPTION OF GOLD FROM LAPE-SUMBAWA ROCKS (INDONESIA) BY HYPOCHLORITE-CHLORIDE	59
<i>Emsal Yanuar, Suprpto</i>	
ANTIFERTILITY COMPOUND FROM THE SEEDS OF CARICA PAPAYA	66
<i>Euis Julaeha, Yunita Permatasari, Tri Mayanti, Ajeng Diantini</i>	
COMPARISON BETWEEN THE CALIBRATION AND THE STANDARD ADDITION METHODS IN DETERMINING DISSOLVED LEAD IN BOROBUDUR'S CONTROL TANKS WATER BY FLAME ATOMIC ABSORPTION SPECTROPHOTOMETRY (F-AAS)	70
<i>Ida Sulistyaningrum, Melati Putri Git Utami, Reni Banowati Istiningrum, Iskandar Muliasir Siregar</i>	
A STUDY OF THE MICROWAVE-ACCELERATED CONDENSATION OF SUBSTITUTED BENZALDEHYDES WITH 3-SUBSTITUTED HYDANTOINS AND THE UNEXPECTED INTERCEPTION OF ALCOHOL PRODUCTS	75
<i>Ika-Wiani Hidayat, Mohan Bhadbhade, Roger W. Read</i>	
THE RELATION OF MITOCHONDRIAL DNA MUTATION WITH MITOCHONDRIAL DISEASES IN CODING REGION	84
<i>Iman P. Maksum, Siti F. Alchumaira, Dian S. Kamara, Saadah D. Rachman, S. Komalaningsih</i>	
DEVELOPMENT AND OPTIMIZATION OF PRE-CONCENTRATION PROCEDURE OF RARE-EARTH ELEMENTS (REES) IN THEIR MINERALS, USING MICROWAVE - ASSISTED SAMPLE DISSOLUTION FOR ICP-ATOMIC EMISSION SPECTROMETRIC DETECTION	93
<i>Iwan Hastiawan, Nicolas H. Bings, J. A. C. Broekaert</i>	
BOND DISSOCIATION ENERGY OF HALOGEN OXIDES	99
<i>Juliandri</i>	
ADSORPTION OF CARBON BLACK USING CHITOSAN IN THE DEINKING PROCESS	106
<i>Muryeti, Estuti Budi Mulyani, Elya Sinurat</i>	
LABEL-FREE ELECTROCHEMICAL DNA BIOSENSOR FOR THE DETECTION OF MYCOBACTERIUM TUBERCULOSIS USING GOLD ELECTRODE MODIFIED BY SELF-ASSEMBLED MONOLAYER OF THIOL	111
<i>Ratna Nurmallasari, Yohan, Shabarni Gaffar, Yeni W. Hartati</i>	

EFFECT OF ISOPROPYL-B-D-THIOGALACTOPYRANOSIDE CONCENTRATION ON PRETHROMBIN-2 RECOMBINAN GENE EXPRESSION IN ESCHERICHIA COLI ER2566	118
<i>Pidinia Raeh Rizkia, Saronom Silaban, Khomaini Hasan, Dian Siti Kamara, Toto Subroto, Soetjoso Soemitro, Iman Permana Maksum</i>	
SYNTHESIS OF TRYPSIN-MODULATING OOSTATIC FACTOR (TMOF) AND ITS ANALOGUES BY SOLID-PHASE PEPTIDE SYNTHESIS USING DIC/OXYMA AS COUPLING REAGENT	125
<i>Rani Maharani, Eka Fitri Yanti, M. Devia Irma Melati, Daniel Sihotang</i>	
AU(III) SELECTIVE ADSORPTION OF QUATERNARY AMMONIUM-SILICA HYBRID IN AU/CU SYSTEM	132
<i>Reni Banowati Istiningrum, Christny Desiree Tiwow, Nuryono, Narsito</i>	
SYNTHESIS AND CHARACTERIZATION OF GADOLINIUM DIETHYLENETRIAMINE PENTAACETATE-FOLATE.....	139
<i>R. P. Fauzia, A. Muthalib, R. U. M. S. Soedjanaatmadja, H. H. Bahti, A. Anggraeni, A. H. Gunawan, H. Pujiastuti, Y. Hidayati</i>	
ANTIOXIDANT AND A-GLUCOSIDASE INHIBITORY COMPOUNDS OF CENTELLA ASIATICA.....	147
<i>Rizna Triana Dewi, Faiza Maryani</i>	
OPTIMIZATION IN MEDIATED ELECTROCHEMICAL OXIDATION USING COBALT SULFATE AS A MEDIATOR.....	153
<i>Rubianto Abd. Lubis, Husein H. Bahti, Iwan Hastiawan, Dennis Mulcahy</i>	
SYNTHESIS AND IN VITRO CYTOTOXICITY OF 1-BENZOYL-3-METHYL THIOUREA DERIVATIVES	157
<i>Ruswanto, Amir M. Miftah, Daryono H. Tjahjono, Siswandono</i>	
PRELIMINARY EVIDENCE OF INOSITOL SUPPLEMENTATION EFFECT ON CELL GROWTH, VIABILITY AND PLASMA MEMBRANE FLUIDITY OF THE YEAST SACCHAROMYCES CEREVISIAE	162
<i>Safri Ishmayana, Ursula J. Kennedy, Robert P. Learmonth</i>	
CYCLIC VOLTAMMETRIC STUDY OF CHROMIUM (VI) AND CHROMIUM (III) ON THE GOLD NANOPARTICLES-MODIFIED GLASSY CARBON ELECTRODE	170
<i>Santhy Wyantuti, Yeni Wahyuni Hartati, Camellia Panatarani, Roekmiati Tjokronegoro</i>	
SECRETORY EXPRESSION OF SACCHAROMYCOPISTIBULIGERA R64 α-AMYLASE WITH NATIVE SIGNAL PEPTIDE IN PICHIA PASTORIS.....	177
<i>Shabarni Gaffar, Dani Permana, Dessy Natalia, Toto Subroto, Soetjoso Soemitro</i>	
THE USE OF DIHEXYLDITHIOCARBAMATE IN SOLVENT EXTRACTION OF TRANSITION METALS	184
<i>Soja Siti Fatimah, Husein H. Bahti, Iwan Hastiawan, Anna Permanasari, Evamarie Hey-Hawkins</i>	
ENCAPSULATION AND STABILITY STUDY OF MONASCUS FERMENTED RICE EXTRACT	189
<i>Sri Priatni</i>	
BAMBOO AS RAW MATERIALS FOR DISSOLVING PULP WITH ENVIRONMENTAL FRIENDLY TECHNOLOGY FOR RAYON FIBER.....	194
<i>Susi Sugesty, Teddy Kardiansyah, Henggar Hardiani</i>	
SAMPLE PREPARATION METHODS FOR ORGANIC ARSENIC SPECIES (ARSENOBETAIN, $(\text{CH}_3)_3\text{AS}^+\text{CH}_2\text{COO}^-$) IN TUNA FISH SAMPLES FOLLOWED BY HG-QFAAS, GF-AAS, AND ICP-MS MEASUREMENTS	200
<i>Tiny Agustini Koesmawati, B. Buchari, Aminudin Sulaeman, Slamet Ibrahim</i>	
SYNTHESIS, CHARACTERIZATION, AND MOLECULAR MODELLING OF BIS(AQUO)TRIS(DIBUTYLDITHIOPHOSPHATO) GADOLINIUM (III)	207
<i>U. Pratomo, A. Anggraeni, A. Muthalib, U. M. S. Soedjanaatmadja, Yuhelda, I. Pinarti, A. T. Hidayat, H. H. Bahti</i>	
DETERMINATION AND CHARACTERIZATION OF PHOTOCATALYTIC PRODUCTS OF LINEAR ALKYL SULPHONATE BY HIGH PERFORMANCE LIQUID CHROMATOGRAPHY AND NUCLEAR MAGNETIC RESONANCE	216
<i>Yeyen Maryani, Indar Kustiningsih</i>	
SYNTHESIS OF CURCUMIN ANALOGUE, N-H AND N-BENZIL-4-PIPERIDONE AND THEIR CYTOTOXIC ACTIVITY.....	224
<i>Yum Eryanti, Rudi Hendra, Tati Herlina, Adel Zamri, Unang Supratman</i>	
Author Index	

3rd International Seminar on Chemistry 2014

The Olefin Reaction between Crude Palm Oil Fatty Acid Methyl Ester (CPO FAME) and Ethylene Using Grubbs II Catalyst

Desnelli^{a,b}, D. Mujahidin^a, Y. Permana^a, C.L. Radiman^{a,*}^a*Inorganic and Physical Chemistry Research Division, Institut Teknologi Bandung, Jalan Ganesha 10, Bandung 40132, Indonesia*^b*Chemistry Department of Universitas Sriwijaya, Jalan Palembang-Prabumulih Km 32 Indralaya, Indonesia*

Abstract

Renewable materials derived from vegetable oils are now widely developed for obtaining green polymers. One of the applications of those polymers is in the field of Enhanced Oil Recovery (EOR) where the polymers are put in the injection wells to increase water viscosity resulting in higher efficiency of oil production. Indonesia is very rich in crude palm oil and therefore, it was chosen as the starting material for polymer synthesis. The objective of this work is to prepare the monomer first, by doing the olefin metathesis reaction between crude palm oil FAME (fatty acid methyl ester) and ethylene. The reaction was carried out using a Grubbs II catalyst in order to obtain methyl 9-decenoate which is used later as the monomer for EOR application. The resulting product was characterized using Nuclear Magnetic Resonance (NMR) and Fourier Transform Infrared (FTIR) spectroscopy as well as Gas Chromatography Mass Spectrometry (GC-MS). Based on the functional group analysis, it was found that methyl 9-decenoate has successfully been synthesized.

Keywords: Crude palm oil, Grubbs II catalyst, methyl 9-decenoate, metathesis.

* Corresponding author. Tel.: +62-22-250-2103; fax: +62-22-250-4154.
E-mail address: cynthia@chem.itb.ac.id.

1. Introduction

Palm oil is one of the vegetable oils which contain unsaturated fatty acids such as oleic acid. The content of oleic acid in palm oil is about 30-40%. Oleochemical industries use oleic acid as the starting material for many important chemical reactions such as olefin metathesis, ozonolysis and epoxidation¹.

Olefin metathesis is an important catalytic reaction in organic synthesis where the internal double bond is converted into new product through the rupture and reformation of C-C double bond². Among other organic reactions, the olefin metathesis reaction gives opportunity to new routes in industries in order to produce petrochemical materials, polymers, oleochemicals and specialty chemicals³. Metathesis reactions use various

transition metal complexes such as tungsten, molybdenum and ruthenium⁴. According to Astruc, the Schrock and Grubbs catalysts are the most efficient catalysts as they are more compatible with functional groups responsible for the metathesis reaction⁵.

Unsaturated fatty acid methyl esters (FAME) and natural oils are renewable feedstock that can be used as starting materials in the metathesis reactions considered as green chemistry⁶. These materials are available abundantly in nature. Indonesia is the largest palm oil producer in the world since its plantations can be found in almost every region of Indonesia.

One of the applications of olefin metathesis is the transformation of internal alkene to terminal alkene via cross metathesis. The objective of this research is to carry out the reaction between unsaturated fatty acid ester (FAME) of crude palm oil and ethylene to produce methyl 9-decenoate monomer. This monomer is an essential chemical for the production of polymer in Enhanced Oil Recovery (EOR) application.

2. Experimental section

2.1. Reagents

Crude palm oil (FAME), Grubbs II catalyst (Sigma), toluene, n-hexane (Merck), activated alumina, silica gel, Mg_2SO_4 , distilled water.

2.2. Procedure

Crude palm oil (CPO) is a reddish vegetable oil obtained from extraction or compression process of palm fruit meat. The crude palm oil (FAME) was first passed through active alumina to remove the impurities present in the crude palm oil (CPO FAME). Then the crude palm oil was put in the reactor and purged with nitrogen gas. Then, the Grubbs II catalyst (with a ratio of 1:500 to crude palm oil) was dissolved in toluene and poured into the reactor. The reactor was then connected to an ethylene pipeline. The metathesis reaction was carried out with ethylene at 10 bars and 50 °C. After a certain time the sample was removed from the reactor. Then water and *n*-hexane were added to the mixture and placed in a separating funnel. The water layer was removed and the organic layer was washed with water twice. The organic layer was poured into a small column of silica to eliminate the excess of catalyst. It was dried afterwards with anhydrate Mg_2SO_4 and filtered. The product was a clear liquid with a characteristic odor. The sample was then characterized by NMR, FTIR and GC-MS spectroscopy.

3. Results and discussion

Figure 1 shows the scheme of metathesis reaction between methyl oleate and ethylene. The Grubbs II catalyst used in this reaction has more tolerance to compounds containing oxygen. Palm oil contains also oxygen that comes from fatty acids. It can be seen that the product of the methyl oleate transformation is methyl 9-decenoate monomer which has a terminal double bond. The side product of this reaction is 1-decene.




Fig. 1. Scheme of metathesis reaction between methyl oleate and ethylene

Figure 2 shows the ^1H -NMR spectrum of the metathesis product. The chemical shift values at 4.98 ppm and 5.77 ppm show a terminal alkene. The peak at chemical shift of 4.98 ppm indicates the presence of protons of $-\text{CH}=\text{CH}_2$ and chemical shift at 5.77 ppm indicates the proton of $-\text{CH}=\text{CH}_2$. The presence of chemical shift near 5.33 ppm is assigned to internal double bond of $-\text{CH}=\text{CH}-$ proton. The presence of internal double bond is derived from the unreacted methyl oleate.




Fig. 2. ^1H -NMR spectrum of metathesis product between CPO FAME and ethylene

The analysis result of ^1H -NMR spectrum was supported by analysis of ^{13}C -NMR spectrum. The ^{13}C -NMR spectrum can be seen in Figure 3. The ^{13}C -NMR spectrum indicates the presence of alkene terminal of methyl 9-decenoate by the appearance of chemical shift at 114.1 ppm and 139.0 ppm. The chemical shift value at 114.1 ppm is assigned to the carbon of $-\text{CH}=\text{CH}_2$. Furthermore, the chemical shift at 139.0 ppm is assigned to the carbon atom of $-\text{CH}=\text{CH}_2$. The presence of chemical shift at 130.3 ppm indicates the presence of internal alkene of methyl oleate residue.




Fig. 3. ^{13}C -NMR spectrum of olefin metathesis product using CPO FAME and ethylene as reactants

The FTIR spectrum of the metathesis product can be seen in Figure 4. The absorption bands at 910 cm^{-1} and 3074 cm^{-1} are assigned to alkene terminals where the terminal double bond is derived from the methyl-9-decenoate. It is concluded that methyl 9-decenoate has been formed by this reaction.






Fig. 4. FTIR spectrum of metathesis product using CPO FAME and ethylene as reactants

The GC-MS spectrum of the reaction product using CPO FAME and ethylene as reactants can be seen in Figure 5. Based on chromatogram GC, the metathesis reaction products showed several peaks. The peak number 3 is the peak of methyl 9-decenoate at a retention time of 4.618 minutes with an area of 13.14%. Unfortunately, the peak number 24 represented the methyl oleate from unreacted CPO FAME is still dominant.



(a)



(b)




Fig. 5. GC-MS spectrum of the metathesis product using CPO FAME and ethylene as reactants (a) GC Chromatogram; (b) MS spectrum of methyl 9-decenoate; (c) MS spectrum from the literature.

Conclusion

We have successfully synthesized the methyl 9-decenoate monomer from CPO FAME using olefin metathesis reaction (ethenolysis reaction) in the presence of Grubbs II catalyst. The presence of methyl 9-decenoate is confirmed by various spectroscopic methods including NMR, FTIR and GC-MS.

Acknowledgements

This work was financially supported by the LPPM-ITB under a contract No. 2259/AL-J/DIPA/PN/SKP/2014; for which the authors are very grateful.

References

1. Mol, J.C., Buffon, R. Metathesis in oleochemistry. *J. Braz. Chem. Soc.* 1998; 9(1), 11-1.
2. Ivin, K.J., Mol, J.C. *Olefin metathesis and metathesis polymerization*. Academic Press; 1997.
3. Mol, J.C. Industrial application of olefin metathesis. *J. Mol. Cat.* 2004, 213, 45- 39.
4. Kaminsky, W, and Fernandes M. New polymers by copolymerization of olefin with bio oil component, *Eur. J. Lipid Sci Technol.* 2008,**110** , 845-841
5. Astruc, D. The metathesis reactions: from a historical perspective to recent developments. *New. J. Chem.* 2005, 29, 56-42.
6. Mol, J.C. Application of olefin metathesis in oleochemistry: An example of green chemistry. *Green Chem.* 2002, 4, 13- 5.

CERTIFICATE

this is to certify that

Desnelli

has attended

The 3rd International Seminar on Chemistry 2014

"Innovations and Advances in Chemistry for the 21st Century Challenges"

held at


Aula Pusat Studi Bahasa Jepang, Jatinangor Campus, Universitas Padjadjaran
20-21 November 2014

as

Presenter


organized by
Department of Chemistry, Faculty of Mathematics and Natural Sciences, Universitas Padjadjaran
in cooperation with
Indonesian Chemical Society

Chairperson of
Organizing Committee



Dr. rer.nat. Iwan Hastiawan

Scientific Committee



Prof. Hideo Hayashi

President of
Indonesian Chemical Society



Muhammad A. Martoprawiro, Ph. D.

Himpunan
Kimia
Indonesia