

Polyoxometalate Intercalated MgAl-Layered Double Hydroxide for Degradation of Malachite Green

by Risfidian Mohadi

Submission date: 22-Dec-2022 08:55PM (UTC+0700)

Submission ID: 1985864667

File name: -Layered_Double_Hydroxide_for_Degradation_of_Malachite_Green.pdf (2.34M)

Word count: 4864

Character count: 26321

¹ Polyoxometalate Intercalated MgAl-Layered Double Hydroxide for Degradation of Malachite Green

Yulizah Hanifah¹, Risfidian Mohadi^{1,2}, Mardiyanto³, Aldes Lesbani^{1,2*}

² Graduate School of Mathematics and Natural Sciences, Faculty of Mathematics and Natural Sciences, Universitas Sriwijaya, Jl. Palembang Prabumulih Km. 32, Oganllir 30662, Indonesia

² Research Center of Inorganic Materials and Coordination Complexes, Faculty of Mathematics and Natural Sciences, Universitas Sriwijaya, Jl. Palembang Prabumulih Km. 32, Oganllir 30662, Indonesia

³ Department of Pharmacy, Faculty of Mathematics and Natural Sciences, Universitas Sriwijaya, Jl. Palembang Prabumulih Km. 32, Oganllir 30662, Indonesia

* Corresponding author's e-mail: aldeslesbani@pps.unsri.ac.id

¹ ABSTRACT

Improving the selectivity of photocatalysis of LDH pristine (MgAl-LDH) and LDH composite (MgAl-SiW₁₂O₄₀] and MgAl-[PW₁₂O₄₀]) was synthesized and used for degraded malachite green (MG). The effects of the amount of catalyst, pH value, and reaction times on degradation performance were discussed. MG degraded better composites than LDH pristine. The results indicated that MgAl-LDH was successfully synthesized by showing the peak diffractions at angles 10.39°(003), 20.17°(006), and 34.8°(009). Both kinds of attained MgAl-[SiW₁₂O₄₀] and MgAl-[PW₁₂O₄₀] had the typical structure of LDH that proved by appeared diffraction at 2θ angles 7.73°, 28.6°, 35.6° for MgAl-[PW₁₂O₄₀] and at 2θ angles 8.61°, 24.27°, 34.96° and 66.34° for MgAl-[SiW₁₂O₄₀]. The FTIR result indicates materials used for fifth regeneration, which confirmed the LDH composite structure. The fotodegradation activity of MG for pristine MgAl LDH (56.1%), composites MgAl-Pw (84.6%) and MgAl-Si (87.8%), respectively. The successful ability of photodegradation process by the percentage of degradation on material LDH-polyoxometalate composite showed the increasing of photodegradation catalytic and the regeneration ability of LDH pristine.

Keywords: LDH, polyoxometalate, photocatalytic, malachite green.

INTRODUCTION

Malachite green (MG) is the primary contaminant in water which are included organic pollutants and an organic dye used in industrial applications, especially in the aquaculture industry, due to as an antibacterial agent. Also used as dye material for wool, paper, leather, etc. on the other side, it has excellent outcomes with adverse effects such as mutagenesis, carcinogenicity also malformation especially for mammals (Salamat et al., 2019). Some contaminants of malachite green with high motilities and toxicities mainly appear contaminant in aquatic organisms and accumulate in plants, which poses a potential risk to the ecosystem and human health (Patel et al., 2019) as a basic dye, malachite green is a toxic cationic

dye, which is cannot efficiently biodegradable, thus BOD₅ in MG is almost to zero (Yong et al., 2014). Thus, its unbiodegradable removal from wastewater should be considered on the environment. Recently, various treatment practices to the removal of MG are adsorption (Burakov et al., 2018), extraction, biological degradation (Nasir et al., 2020) and application on photodegradation (Shahzad et al., 2016) have been used to reduce contaminants from wastewater (Gupta et al., 2018). Photocatalysis, a green treatment technology, is considered one of the most promising technologies because of its low cost, satisfactory performance, and high efficiency (Shi et al., 2019 and Lu et al., 2020). The photodegradation process is still considered as most favorable to remove dyes from water, thus of its high efficient

and simply eliminate (Nazir et al., 2020). The photocatalyst have been applied to eliminate dyes from aqueous, such as, industrial, activated carbon, biological waste materials and porous carbon (Zhang et al., 2018).

Layered double hydroxide (LDH) consisting of brucite-like layers with positively charged multimetal cations and interlayer compensating anion, have been applied to eliminate pollutants. LDH has general formula $M^{2+}_x M^{3+}_{3-x} (OH)_2 A^{n-}_{x/(3-x)}$ where M^{2+} and M^{3+} are divalent metal cations (Ca, Mg, Co, Cu, Ni, Mn) and trivalent metals (Al, Fe, Cr). The value of x is equal to the molar ratio of $M^{3+}/(M^{2+}+M^{3+})$, where the value is between 0.20 and 0.33; and A is the anion that is between the layers of valence n (Cl^- , NO_3^- , ClO_4^- , CO_3^{2-} , SO_4^{2-} and so on) (Malherbe & Besse, 2000). Recently, LDH research has been related to adsorbents to remove pollutants from wastewater (organic and inorganic), energy storage and heavy metal ion (Yoshida et al., 2015; Behbahani et al., 2020). Single LDH is not considered an efficiently catalyst due to its morphology (Kaul et al., 2016). The structural characteristics of LDHs direct to the manipulation of morphology and active centers (such as electronic states, crystal faces, and defects) via various control synthesis techniques such as intercalated, immobilized etc, thereby significantly gaining performance of catalytic (Tonda et al., 2018 and Wang et al., 2019).

Thus, the current study report on the application of LDH as a photocatalyst that degrades organic pollutants have been synthesized with various compounds. According to Yulisari et al. (2022) reported that modified LDH (ZnAl and MgAl) with metal oxide (ZnO and TiO_2) as a catalyst for degrading malachite green, which is informed that LDH composite has better performance than LDH pristine. According to Gholami et al., (2020) Combining biochar with Zn-Co-LDH was composited for photocatalytic removal of gemifloxacin antibiotic. Sun et al. (2021) successfully synthesized NiCo-LDH composited with transition metal phosphide (Ni_2P) on degrade tetracycline to improve photocatalytic activity. Guo et al. (2021) reported their composite synthesis show the stronger degradation and inform the predominant photocatalytic performance on composite $CoAl-CeO_2$. Amini et al. (2017) informed the success in the synthesis LDH with anionic POM that was used for degradation dye which are rhodamine-B and methylene blue, the percentage of degradation reached 97% and




Figure 1. The structure of the malachite green (MG)

99%. LDHs have diverse morphological advantages and adjustable compositions, such as an interlayered arrangement of mortal ions, and broad chemical compositions and ability to exchange anions on these layers (Hu et al., 2019) and LDH materials have high tunable band gap and adsorption capacity which are capable for cation-anion-exchange and provide spatially separated redox reaction sites (Mohapatra et al., 2016).

In the present study, MgAl pristine and MgAl composite which was composited with two different polyoxometalate (POM) type Keggin $K_3[\alpha-PW_{12}O_{40}]$ and $K_4[\alpha-SiW_{12}O_{40}]$ were synthesized using co-precipitation method and their photocatalytic performances were investigated such as the effect of pH, catalyst loading, contact time and regeneration of material. We select POM as intercalate to composite with MgAl-LDH due to POM anions have high negative charge for increasing the performance capability for cationic dye, that can endow the function of photodegradation malachite green (MG) dye. The material is applied as a photocatalyst to degrade MG dye. The prepared material were characterized using FTIR, XRD, SEM and UV-DRS. Furthermore, application as a photocatalyst in this study carried out the photodegradation process such as the effect of pH, catalyst loading, contact time and regeneration of material.

EXPERIMENTAL

Chemical and instrumentation

Magnesium nitrate, zinc nitrate, aluminium nitrate, sodium phosphate, sodium tungstate, sodium carbonate, sodium hydroxide and hydrogen chloride were used in this research. Malachite green (MG) is one of the

synthetic dyes which has formula $C_{23}H_{25}ClN_2$ (4-[(4-dimethylaminophenyl)-phenyl-methyl]-N) and maximum absorbance at λ_{max} 616 nm. Characterization of materials was carried using Shimadzu FTIR Prestige-21. Analysis of XRD was conducted out by Rigaku XRD Mini-15-6000 diffractometer. The degradation of MG was analyzed by UV-Vis Biobase BK-UV 1800 PC spectrophotometer at 617 nm. UV-Vis Diffuse Reflectance Spectrometer for band gap analysis was carried out using JASCO V-760 and for SEM analysis was conducted by using SEM FEI Quanta 650. Polyoxometalate $K_3[\alpha-PW_{12}O_{40}] \cdot nH_2O$ and $K_4[\alpha-SiW_{12}O_{40}] \cdot nH_2O$ were synthesized according to previous reported literatures (Lesbani et al., 2014).

Synthesis of MgAl/LDH

An amount of 18.75 g Zinc Nitrate 0.75 M mixed in water (100 mL) and 9.3 g aluminum nitrate 0.25 M dissolved in water (100 mL) in a stirrer for 2 hours. MgAl-LDH was synthesized by a modified coprecipitation method by Lesbani et al. (2021). The pH of the mixture was adjusted to pH 10 by adding sodium hydroxide (2M). This mixture was stirred for 6 hours at 85 °C. The resulting product was washed and dried using an oven at a temperature of 110 °C then the MgAl LDH was weighed.

Preparation of composite

The composite were prepared by adding a solution A (1 g of polyoxometalate compound on 50 mL of distilled water) and solution as B (2 g of LDH with 25 mL of 1 M NaOH). The suspension is mixed rapidly under conditions of N_2 gas for 24 hours and then a product washed and dried. Characterization the results of the intercalation material will be carried out using XRD analysis, FT-IR spectrophotometer, SEM analysis and UV-DRS.

Photocatalytic study

The composite was applied to degrade dye malachite green solutions. Firstly, using optimum catalyst weight with 20 mg/L malachite green was placed in the dark condition and magnetically stirred for 30 achieve a desorption equilibrium. For the photocatalytic test applied at a certain time interval, 20 mL of the suspension with 20 mg/L malachite green. Optimization degradation includes variations in pH at range (1, 3, 5, 7 and

9), for catalysts loading at 0.075, 0.1, 0.25, 0.5, and 0.75 g respectively and degradation contact time at 10, 20, 30, 40, 50, 60, 70, 80, 90, 100, 110, and 120 minutes. This degradation process is implemented using UV light. The percentage of degradation is defined based on the following equation formula: Percentage of Degradation (%) = $(C_0 - C_t) / C_0 \times 100$, where C_0 is the initial dye concentration and C_t is the dye concentration after degradation (Hadnadjev-Kostic et al., 2017).

Regeneration experiment

In order to examine the reproducibility of the photocatalyst, the suspension after first reaction (2.4) was centrifuged to collect a solid powder. The suspension was precipitate and separate from the solution. Then, the precipitate powder was dried at 70 °C for 24 h. The solid powder was subjected to the next photocatalytic reaction. The above procedure was repeated fifth time to confirm the repeatability of both LDH pristine and LDH composite photoacatalyst.

RESULTS AND DISCUSSION

LDH-based materials


Figure 2 shows stepwise preparation synthesized catalyst. FT-IR analysis was utilized to determine the surficial groups of LDH. The composites were successfully synthesized. The characterization by FT-IR was also carried out on LDH pristine and LDH composite, it is all described on Figure 2. The FTIR spectrum showed a band between 3420–3500 cm^{-1} , which was indicated from brucite-like layers and interlayer water molecules. Interlayer water also gives medium-intensity (H_2O) absorption close to 1630 cm^{-1} . The 1381 cm^{-1} band represents CO_3 vibrations (Zhao et al., 2018). The ν_{OH} and W-O-W bands are in the band 983–870 cm^{-1} and 804.84 cm^{-1} respectively (Wang et al., 2008). Figure 2 shows that these bands are still present in their typical LDH on catalyst LDH-polyoxometalate.

The MgAl-LDH and LDH composites were estimated by XRD on Figure 3. The result shows that the main components of LDH structure is that indicated angles 2θ at 10.39°(003), 20.17°(006), and 34.8°(009). Liu et al. (2022) when XRD patterns show the reflection of (006), (009), (012), (110) and (113), which can be indexed typically

of LDH materials, indicating its MgAl-LDH has been successfully (Zhou et al., 2020). The original diffraction of polyoxometalate compound $K_4[\alpha\text{-SiW}_{12}\text{O}_{40}]$, $K_3[\alpha\text{-PW}_{12}\text{O}_{40}]$ was shown at 2θ angles of $5\text{--}10^\circ$, $10\text{--}20^\circ$, $25\text{--}30^\circ$ (Wang et al., 2008). Due to the use of both polyoxometalate on MgAl-LDH as composite LDH. Based on Figure 3, both peaks are still present of each type of

polyoxometalate in $\text{MgAl}[\text{PW}_{12}\text{O}_{40}]$ that was at angles 7.73° , 28.6° , 35.6° . on the other hand, the presence of $K_4[\alpha\text{-SiW}_{12}\text{O}_{40}]$ in LDH is indicated at 2θ angles 8.61° , 24.27° , 34.96° and 66.34° . The composites were successfully synthesized.

The morphology of as-prepared MgAl-LDH was investigated by SEM analysis, as shown in Figure 4. Morphology can be observed for all



6

Figure 2. FTIR spectra of catalyst a) MgAl-LDH b) $K_3[\alpha\text{-PW}_{12}\text{O}_{40}]$ c) $K_4[\alpha\text{-SiW}_{12}\text{O}_{40}]$ d) $\text{MgAl}[\text{PW}_{12}\text{O}_{40}]$ and e) $\text{MgAl}[\text{SiW}_{12}\text{O}_{40}]$







Figure 3. Diffractogram of catalyst a) MgAl-LDH b) $K_3[\alpha\text{-PW}_{12}\text{O}_{40}]$ c) $K_4[\alpha\text{-SiW}_{12}\text{O}_{40}]$ d) $\text{MgAl}[\text{PW}_{12}\text{O}_{40}]$ and d) $\text{MgAl}[\text{SiW}_{12}\text{O}_{40}]$



a)



b)



c)



Figure 4. SEM of (a) MgAl-LDH (b) MgAl-[SiW₁₂O₄₀].nH₂O (c) MgAl-[PW₁₂O₄₀].nH₂O

MgAl-LDH samples, which validates LDH microsphere to the layered structure. LDH pristine and LDH composite their respective heterostructures. When LDH intercalated heterostructure is

observed, a morphology that seems to result from the assembly of both layered materials is evidence. The morphology structure on synthesizing [SiW₁₂O₄₀] which showed aggregate appearing in the surface material (Hanifah et al., 2022). It is possible to appreciate the existence of a platelet-shaped microcrystal. It can be seen that the LDH composite compared with LDH pristine, was polyporous, which implied adding polyoxometalate into the mixture solution can stick to the surface of the LDH composite. EDX analysis in Table 1 shows the percentages of Ni, Al, W, P, Si, K, Cl, C, O and Na atoms. W appears after compositing into MgAl-[SiW₁₂O₄₀] and MgAl-[PW₁₂O₄₀].

Effect of optimization variables on malachite green degradation

The presence of polyoxometalate on Mg degradation on pH in both composite MgAl-[SiW₁₂O₄₀] and MgAl-[PW₁₂O₄₀] can affect the stability of LDH structure. Enhancing the abundant of anionic can give the ability to form positively charged electron holes especially media on pH less than 7 that are effective in creating OH• radicals which has the capability to degrade dye stuff but also cause photodecomposition of polyoxometalate into ions. There is photocatalytic reaction UV irradiated catalyst MgAl-POM will produces a hole (h_{vb}⁺) and electrons (e_{cb}⁻) H₂O will form a hydroxyl radical (•OH) which able to degrade malachite green became simply intermediate. Process mechanism photocatalysis using MgAl-POM is shown at the following stage:



This causes in this study MgAl-LDH was obtained at pH 7 while pH 1 for K₃[α-PW₁₂O₄₀] and pH 1 K₄[α-SiW₁₂O₄₀], while MgAl-[PW₁₂O₄₀] is optimum at pH 3.2 and MgAl-[SiW₁₂O₄₀] is optimum at pH 7. Figure 6 shows the effect pH on degrading malachite green by catalysts both LDH pristine and LDH composite. Catalysts loading on the degradation process also were examined in this study by implementing at the optimum pH in 120 minutes. Figure 7 show the results of various catalysts loading on degrading malachite green

Table 1. EDX of catalysts

Element	MgAl-LDH (%wt)	MgAl-Pw (%wt)	MgAl-Si (%wt)
Mg	8.14	6.32	2.51
Al	5.20	6.85	1.62
W	-	2.15	32.54
P	-	-	7.82
Si	-	-	-
K	-	-	3.53
Cl	-	-	9.17
C	13.57	7.98	8.20
O	51.39	45.85	28.78
Na	2.58	4.1	5.83
N	9.12	-	-




Figure 5. Process mechanism photocatalysis using MgAl-POM

process by both LDH composite and LDH pristine, where it can be seen that MgAl-[PW₁₂O₄₀] and MgAl-[SiW₁₂O₄₀] have a degradation percentage that was not much different. Figure 7 shows the effect of variations in MG degradation time by LDH composite and LDH pristine. The value of C/C₀ during 120 minutes of treatment had increased then with increasing time the amount of

MG degraded increased. The percent MG degradation for MgAl-LDH, MgAl-[PW₁₂O₄₀], MgAl-[SiW₁₂O₄₀] was 56.9%, 84.6%, 87.9%, respectively. The percent degradation for K₃[α-PW₁₂O₄₀] and K₄[α-SiW₁₂O₄₀] was 83%, 74.6%, respectively. It appears from the results of the percentage degradation that the catalyst LDH composite has a better ability to degrade MG than LDH pristine.

Regeneration of catalyst

The use of the catalyst is expected to be efficient so that it can be used repeatedly to degrade organic pollutants. This ability is known from the decrease in degradation percentage after several cycles of repeated use. Figure 8 shows a slight decrease in the degradation ability after the reuse of composite as a photocatalyst. After 5 cycles of




Figure 6. Effect of pH on MG degradation by catalysts






Figure 7. Effect of a) times and b) catalysts weight on MG degradation by catalysts

using the catalyst there was a decrease %degradation of MgAl-LDH 46.1%. The decrease in %degradation of LDH composite after 5 cycles of use by MgAl-[$PW_{12}O_{40}$] and MgAl-[$SiW_{12}O_{40}$] were 78.4% and 80.4%, respectively. The reusability of LDH pristine and LDH composite corresponded to the %degradation and apparent rate value. From the results of reusability, it can be seen that the MgAl-[$SiW_{12}O_{40}$] was better than the MgAl-[$PW_{12}O_{40}$]. Figure 6 shows the spectra FTIR of all materials MgAl-LDH, $K_4[\alpha-SiW_{12}O_{40}]$, $K_3[\alpha-PW_{12}O_{40}].nH_2O$, MgAl-[$SiW_{12}O_{40}$] and MgAl-[$PW_{12}O_{40}$]. The representation of stretching and bending vibration of FTIR spectra confirmed the good formation of MgAl-LDH, $K_4[\alpha-SiW_{12}O_{40}]$, $K_3[\alpha-PW_{12}O_{40}]$, and both MgAl-[$SiW_{12}O_{40}$] and

MgAl-[$PW_{12}O_{40}$]. The characterization by FTIR spectrum was also carried out on LDH composite that had to degrade MG to show the alteration after regeneration. The spectrum showed a band between 3420–3500 cm^{-1} and about 1630–1583.6 cm^{-1} offering the stretching vibration of the hydroxyl groups along the stretching vibration of an interlayer water molecule. The peak at 1359 cm^{-1} also represents the intercalated NO_3^- bending vibration [46]. The W-O and W-O-W bands are in the 985.4 cm^{-1} and 856.3 cm^{-1} , meaning characteristic of polyoxometalate. It also shows that band on MgAl-[$PW_{12}O_{40}$] are 795.4 [47]. IR spectra data [$PW_{12}O_{40}$] have remained in the MgAl-LDH. Figure 10 shows that these bands are still present for the catalyst that has degraded MG.

Table 2. The value of %degradation malachite green

Catalyst	% degradation malachite green	Ref.
TiO ₂ /ZnO	69	Mohamed et al. (2018).
TiO ₂ nanotubes	80	Prado et al. (2009)
Pc/ZSWP	79.2	Gupta et al. (2015)
CH/ZnO	54	Saad et al. (2020)
Guar gum/Al ₂ O ₃	80	Pathania et al. (2016)
FeTiO ₂	77	Asilturk et al. (2009)
MgAl-[PW ₁₂ O ₄₀]	84.6	In this study
MgAl-[SiW ₁₂ O ₄₀]	87.8	In this study

**Figure 8.** Regeneration of catalyst in the fifth cycle**Figure 9.** Spectra FTIR after regeneration 5 cycle

CONCLUSIONS

The LDH pristine and LDH composite has been successfully prepared and used for photodegradation MG. The materials synthesized optimally were well-oriented layer structures based on the characterization results. Modifying of MgAl-LDH materials, which form composites with both polyoxometalate $K_3[\alpha-PW_{12}O_{40}]$ and $K_4[\alpha-SiW_{12}O_{40}]$ resulted in an enhanced capability for photodegradation of cationic dyes MG. Both composite MgAl- $[PW_{12}O_{40}]$ and MgAl- $[SiW_{12}O_{40}]$ composites also improved the regeneration performance of MG degradation compared to MgAl-LDH. The characterization results after fifth cycle regeneration using FTIR of materials that have degraded MG show that LDH pristine still has an LDH structure, and LDH composite also still has LDH and polyoxometalate structure. The result of the investigation carried out according to pH, catalyst loading, and optimum contact time showed %degradation, degradation rate, and reusability of MgAl- $[PW_{12}O_{40}]$ and MgAl- $[SiW_{12}O_{40}]$ composites were better than LDH pristine. MgAl- $[SiW_{12}O_{40}]$ composite has better performance activity, band gap energy, and reusability degradation than MgAl- $[PW_{12}O_{40}]$.

18

Acknowledgements

This research was supported by the Ministry of Education, Culture, Research and the Technology Republic Indonesia Through Dik 31 Hibah Disertasi Doktor with main contract no. 142/E5/PG.02.00. PT/2022 and derivative contract no. 0145.005/UN.9.3.1/PL/2022. The authors also thank the Research Center of Inorganic Materials and Complexes FMIPA Universitas Sriwijaya for valuable discussion, apparatus, and chemical analysis.

REFERENCES

1. Abu, S., Byzinski, G., Ribeiro, C. 2016. Synergistic effect on the photocatalytic activity of N-doped TiO_2 nanorods synthesised by novel route with exposed (110) facet. *Journal of Alloys and Compounds*, 666, 38–49.
2. Amini, M., Khaksar, M., Ellern, A., Keith Woo, L. 2018. A new nanocluster polyoxomolybdate $[Mo_{36}O_{110}(NO)_4(H_2O)_{14}] \cdot 52H_2O$: Synthesis, characterization and application in oxidative degradation of common organic dyes. *Chinese Journal of Chemical Engineering*, 26, 337–342.
3. Asiltürk, M., Sayılkan, F. 2009. Effect of Fe^{3+} ion doping to TiO_2 on the photocatalytic degradation of Malachite Green dye under UV and vis-irradiation. *Journal of Photochemistry and Photobiology A : Chemistry*, 203, 64–71.
4. Behbahani, E.S., Dashtian, K., Ghaedi, M. 2019. Fe/Co-chalcogenide-stabilized Fe_3O_4 nanoparticles supported MgAl-layered double hydroxide as a new magnetically separable sorbent for the simultaneous spectrophotometric determination of anionic dyes. *Microchemical Journal*, 104431.
5. Burakov, A.E., Galunin, E. V., Burakova, I. V., Kucherova, A.E., Agarwal, S., Tkachev, A.G., Gupta, V.K. 2018. Ecotoxicology and Environmental Safety Adsorption of heavy metals on conventional and nanostructured materials for wastewater treatment purposes : A review. *Ecotoxicology and Environmental Safety*, 148, 702–712.
6. Fernandes, A.J.S., Sodr, W.C., Bezerra, B., Rojas, A., Perez-carvajal, J., Alc, A.C.S. 2021. In situ assembling of layered double hydroxide to magadiite layered silicate with enhanced photocatalytic and recycling performance. *Applied Surface Science*, 569, 151007.
7. Gholami, P., Khataee, A., Darvishi, R., Soltani, C., Dinpazhoh, L. 2020. Photocatalytic degradation of gemifloxacin antibiotic using Zn-Co-LDH @biochar nanocomposite. *Journal of Hazardous Materials*, 382, 121070.
8. Guo, X., Fan, Z., Wang, Y., Jin, Z. 2021. CeO_2 nanoparticles dispersed on CoAl-LDH hexagonal nanosheets as 0D/2D binary composite for enhanced photocatalytic hydrogen evolution. *Surfaces and Interfaces*, 24, 101105.
9. Gupta, A., Pandey, O.P. 2018. Visible irradiation induced photodegradation by NbC/C nanocomposite derived from smoked cigarette litter (filters). *Solar Energy*, 163, 167–176.
10. Hadnadjev-Kostic, M., Vulic, T., Marinkovic-Neducin, R., Lončarević, D., Dostanić, J., Markov, S., Jovanović, D. 2017. Photo-induced properties of photocatalysts: A study on the modified structural, optical and textural properties of TiO_2 -ZnAl layered double hydroxide based materials. *Journal of Cleaner Production*, 164, 1–18.
11. Hanifah, Y., Mohadi, R., Mardiyanto, M., Lesbani, A. 2022. Photocatalytic Degradation of Malachite Green by NiAl-LDH Intercalated Polyoxometalate Compound. *Bulletin of Chemical Reaction Engineering & Catalytic*, 17.
12. Haris, M., Khan, M.W., Paz-Ferreiro, J., Mahmood, N., Eshtiaghi, N. 2022. Synthesis of functional hydrochar from olive waste for simultaneous removal of azo and non-azo dyes from water. *Chemical Engineering Journal Advances*, 9, 100233.
13. Jo, W.K., Kim, Y.G., Tonda, S. 2018. Hierarchical

- flower-like NiAl-layered double hydroxide microspheres encapsulated with black Cu-doped TiO₂ nanoparticles: Highly efficient visible-light-driven composite photocatalysts for environmental remediation. *Journal of Hazardous Materials*, 357, 19–29.
14. Juleanti, N., Palapa, N.R., Taher, T., Hidayati, N., Putri, B.I., Lesbani, A. 2021. The capability of biochar-based CaAl and MgAl composite materials as adsorbent for removal Cr(VI) in aqueous solution. *Science and Technology Indonesia*, 6, 196–203.
15. Kaul, P.K., Samson, A.J., Selvan, G.T., Enoch, I., Selvakumar, P.M. 2016. Synergistic effect of LDH in the presence of organophosphate on thermal and flammable properties of an epoxy nanocomposite. *Applied Clay Science*, 135, 234–243.
16. Lesbani, A., Mohadi, R. 2014. Brønsted acid of Keggin type polyoxometalate catalyzed pinacol rearrangement. *Bulletin of Chemical Reaction Engineering and Catalysis*, 9, 136–141.
17. Li, Q., Kang, Z., Mao, B., Wang, E., Wang, C., Tian, C., Li, S. 2008. One-step polyoxometalate-assisted solvothermal synthesis of ZnO microspheres and their photoluminescence properties. *Materials Letters*, 62, 2531–2534.
18. Liu, X., Lu, J., Fu, M., Zheng, H., Chen, Q. 2022. Activated carbon induced hydrothermal carbonization for the treatment of cotton pulp black liquor. *Journal of Water Process Engineering*, 47, 102733.
19. Lu, Y., Jiang, B., Fang, L., Ling, F., Gao, J., Wu, F. 2016. Chemosphere High performance NiFe layered double hydroxide for methyl orange dye and Cr (VI) adsorption. *Chemosphere*, 152, 415–422.
20. Lv, X., Qin, X., Wang, K., Peng, Y., Wang, P., Jiang, G. 2019. Nanoscale zero valent iron supported on MgAl-LDH-decorated reduced graphene oxide: Enhanced performance in Cr(VI) removal, mechanism and regeneration. *Journal of Hazardous Materials*, 373, 176–186.
21. Magdy, A., Abukhadra, M.R., Ahmed, S.A., Elzanaty, A.M., Mady, A.H., Betiha, M.A., Shim, J., Rabie, A.M. 2020. Photocatalytic degradation of malachite green dye using chitosan supported ZnO and Ce – ZnO nano-flowers under visible light. *Journal of Environmental Management*, 258, 110043.
22. Malherbe, F., Besse, J.P. 2000. Investigating the effects of guest-host interactions on the properties of anion-exchanged Mg-Al hydrotalcites. *Journal of Solid State Chemistry*, 155, 332–341.
23. Mohammed, N.A.S., Abu-Zurayk, R.A., Hamadneh, I., Al-Dujaili, A.H. 2018. Phenol adsorption on biochar prepared from the pine fruit shells: Equilibrium, kinetic and thermodynamics studies. *Journal of Environmental Management*, 226, 377–385.
24. Mohapatra, L., Parida, K.M. 2012. Zn-Cr layered double hydroxide: Visible light responsive photocatalyst for photocatalytic degradation of organic pollutants. *Separation and Purification Technology*, 91, 73–80.
25. Nayak, S., Parida, K.M. 2016. Nanostructured CeO₂/MgAl-LDH composite for visible light induced water reduction reaction. *International Journal of Hydrogen Energy*, 41, 21166–21180.
26. Pathania, D., Katwal, R., Sharma, G., Naushad, M., Khan, M.R., Al-muhtaseb, A.H. 2016. Novel guar gum/Al₂O₃ nanocomposite as an effective photocatalyst for the degradation of malachite green dye. *International Journal of Biological Macromolecules*, 87, 366–374.
27. Salamat, S., Hadavifar, M., Rezaei, H. 2019. Journal of Environmental Chemical Engineering Preparation of nanochitosan-STP from shrimp shell and its application in removing of malachite green from aqueous solutions. *Journal of Environmental Chemical Engineering*, 7, 103328.
28. Shi, W., Ren, H., Huang, X., Li, M., Tang, Y., Guo, F. 2020. Separation and Purification Technology Low cost red mud modified graphitic carbon nitride for the removal of organic pollutants in wastewater by the synergistic effect of adsorption and photocatalysis. *Separation and Purification Technology*, 237, 116477.
29. Sun, Y., Wang, L., Wang, T., Liu, X., Xu, T., Wei, M., Yang, L., Li, C. 2021. Improved photocatalytic activity of Ni₂P/NiCo-LDH composites via a Co e P bond charge transfer channel to degrade tetracycline under visible light. *Journal of Alloys and Compounds*, 852, 156963.
30. Sun, X., Dong, J., Li, Z., Liu, H., Jing, X., Chi, Y., Hu, C. 2019. Mono-transition-metal-substituted polyoxometalate intercalated layered double hydroxides for the catalytic decontamination of sulfur mustard simulant. *Dalton Transactions*, 48, 5285–5291.
31. Wang, J.A., Chen, L.F., Noreña, L.E. 2008. Al-MCM-41 and Pt / H₃PW₁₂O₄₀ / Al-MCM-41 : structure characterization and catalytic properties. *Studies in Surface Science and Catalysis*, 174, 1259–1262.
32. Yin, Q., Wang, R., Zhao, Z. 2018. Application of Mg–Al-modified biochar for simultaneous removal of ammonium, nitrate, and phosphate from eutrophic water. *Journal of Cleaner Production*, 176, 230–240.
33. Yoshida, M., Koilraj, P., Qiu, X., Hirajima, T., Sasaki, K. 2015. Sorption of arsenate on MgAl and MgFe layered double hydroxides derived from calcined dolomite. Elsevier BV.
34. Yong, L., Zhanqi, G., Yuefei, J., Xiaobin, H., Cheng, S., Shaogui, Y. 2015. Photodegradation of malachite green under simulated and natural irradiation : Kinetics, products , and pathways. *Journal of Hazardous Materials*, 285, 127–136.
35. Yuliasari, N., Wijaya, A., Amri, A., Mohadi, R., Elfita, E., Lesbani, A. 2022. Application of M²⁺ (Magnesium, Zinc)/Alumina-Metal Oxide Composites as Photocatalysts for the Degradation of Cationic Dyes. *Ecological Engineering & Environmental Technology*, 23, 125–135.

36. Zhang, S., Yan, Y., Wang, W., Gu, X., Li, H., Li, J. 2017. Intercalation of phosphotungstic acid into layered double hydroxides by reconstruction method and its application in intumescent flame retardant poly (lactic acid) composites Intercalation of phosphotungstic acid into layered double hydroxides by recons. *Polymer Degradation and Stability*, 147, 142–150.
37. Zhou, H., Wu, F., Fang, L., Hu, J., Luo, H. 2020. Layered NiFe-LDH/MXene nanocomposite electrode for high-performance supercapacitor. *International Journal of Hydrogen Energy*, 45, 13080–13089.
38. Prado, A.G.S., Costa, L.L. 2009. Photocatalytic decoloration of malachite green dye by application of TiO₂ nanotubes. *Journal of Hazardous Materials*, 169, 297–301.

Polyoxometalate Intercalated MgAl-Layered Double Hydroxide for Degradation of Malachite Green

ORIGINALITY REPORT

25%

SIMILARITY INDEX

17%

INTERNET SOURCES

16%

PUBLICATIONS

4%

STUDENT PAPERS

PRIMARY SOURCES

1

doaj.org

Internet Source

6%

2

Submitted to Sriwijaya University

Student Paper

2%

3

Weilong Shi, Hongji Ren, Xiliu Huang, Mingyang Li, Yubin Tang, Feng Guo. "Low cost red mud modified graphitic carbon nitride for the removal of organic pollutants in wastewater by the synergistic effect of adsorption and photocatalysis", Separation and Purification Technology, 2020

Publication

1%

4

Rozalya Alhunity, Salah Aljbouir, Emad El Qada. "Life Cycle Assessment of Asphalt Mix Containing Jordanian Oil Shale Ash", Ecological Engineering & Environmental Technology, 2023

Publication

1%

5

pubs.rsc.org

Internet Source

1%

6

ebin.pub

Internet Source

1 %

7

Lan Wang, Zhiqiang Zhu, Fu Wang, Yihao Qi, Wei Zhang, Chuanyi Wang. "State-of-the-art and prospects of Zn-containing layered double hydroxides (Zn-LDH)-based materials for photocatalytic water remediation", Chemosphere, 2021

Publication

1 %

8

Muhammad Altaf Nazir, Muhammad Aswad Bashir, Tayyaba Najam, Muhammad Sufyan Javed et al. "Combining structurally ordered intermetallic nodes: Kinetic and isothermal studies for removal of malachite green and methyl orange with mechanistic aspects", Microchemical Journal, 2021

Publication

1 %

9

www.mdpi.com

Internet Source

1 %

10

Nawal Taoufik, M'hamed Sadiq, Mohamed Abdennouri, Samir Qourzal, Alireza Khataee, Mika Sillanpää, Noureddine Barka. "Recent advances in the synthesis and environmental catalytic applications of layered double hydroxides-based materials for degradation of emerging pollutants through advanced oxidation processes", Materials Research Bulletin, 2022

1 %

11

www.sciencetechindonesia.com

Internet Source

1 %

12

Antonio J. S. Fernandes Júnior, Welton C. Sodr , B rbara E. C. F. Soares, C cero W. B. Bezerra et al. "In situ assembling of layered double hydroxide to magadiite layered silicate with enhanced photocatalytic and recycling performance", Applied Surface Science, 2021

Publication

1 %

13

Snehaprava Das, Kulamani parida. "Superior photocatalytic performance of Co Al LDH in the race of metal incorporated LDH: A comparison study", Materials Today: Proceedings, 2020

Publication

1 %

14

researchspace.ukzn.ac.za

Internet Source

1 %

15

www.ect-journal.kz

Internet Source

1 %

16

C. Barriga, M. Gait n, I. Pavlovic, M. A. Ulibarri, M. C. Hermos n, J. Cornejo. "Hydrotalcites as sorbent for 2,4,6-trinitrophenol: influence of the layer composition and interlayer anion", Journal of Materials Chemistry, 2002

Publication

<1 %

- | | | |
|----|--|------|
| 17 | Risfidian Mohadi, Patimah Mega Syah Bahar Nur Siregar, Neza Rahayu Palapa, Tarmizi Taher, Aldes Lesbani. "Layered Double Hydroxide/Chitosan Composite (Mg-Al/CT) as a Selective Adsorbent in Congo Red Adsorption from Aqueous Solution", Ecological Engineering & Environmental Technology, 2022
Publication | <1 % |
| 18 | api.intechopen.com
Internet Source | <1 % |
| 19 | mdpi-res.com
Internet Source | <1 % |
| 20 | Submitted to National Institute of Technology, Rourkela
Student Paper | <1 % |
| 21 | Luna Silaen, Elfita Elfita, Risfidian Mohadi, Normah Normah, Novie Juleanti, Neza Palapa, Aldes Lesbani. "Soft Ion Divalent Metals toward Adsorption on Zn/Al-POM Layered Double Hydroxide", Journal of Ecological Engineering, 2021
Publication | <1 % |
| 22 | He Guo, Yawen Wang, Liuni Liao, Zhen Li et al. "Review on remediation of organic-contaminated soil by discharge plasma: Plasma types, impact factors, plasma-assisted | <1 % |

23

Arini Fousty Badri, Novie Juleanti, Risfidian Mohadi, Mardiyanto Mardiyanto, Aldes Lesbani. "The Efficiency of Mg-Al/Biochar for Methyl Orange and Methyl Red Removal", Ecological Engineering & Environmental Technology, 2022

Publication

24

Mega Mutiara Sari, Iva Yeniz Septiariva, Tendra Istanabi, Sapta Suhardono et al. "Comparison of Solid Waste Generation During and Before Pandemic Covid-19 in Indonesia Border Island (Riau Islands Province, Indonesia)", Ecological Engineering & Environmental Technology, 2023

Publication

25

Dinusha Peramune, Danushika C. Manatunga, Rohan S. Dassanayake, Vikum Premalal et al. "Recent advances in biopolymer-based advanced oxidation processes for dye removal applications: A review", Environmental Research, 2022

Publication

26

Samaneh Salamat, Mojtaba Hadavifar, Hassan Rezaei. "Preparation of nanochitosan-STP from shrimp shell and its application in

<1 %

<1 %

<1 %

<1 %

removing of malachite green from aqueous solutions", Journal of Environmental Chemical Engineering, 2019

Publication

27

Kovar, P.. "Layered double hydroxide intercalated with p-methylbenzoate and p-bromobenzoate: Molecular simulations and XRD analysis", Journal of Colloid And Interface Science, 20080301

Publication

<1 %

28

link.springer.com

Internet Source

<1 %

29

Debao Wang, Caixia Song. "Controllable Synthesis of ZnO Nanorod and Prism Arrays in a Large Area", The Journal of Physical Chemistry B, 2005

Publication

<1 %

30

Li, D.. "Preparation of 5-benzotriazolyl-4-hydroxy-3-sec-butylbenzenesulfonate anion-intercalated layered double hydroxide and its photostabilizing effect on polypropylene", Journal of Solid State Chemistry, 200610

Publication

<1 %

31

Sisnayati Sisnayati, Muhammad Said, Nabila Aprianti, Ria Komala, Hendra Dwipayana, Muhammad Faizal. "Metal Pillared Bentonite Synthesis and its Characteristics Using X-Ray

<1 %

Diffraction", Journal of Ecological Engineering, 2022

Publication

32

core.ac.uk

Internet Source

<1 %

33

dspace.iua.edu.sd

Internet Source

<1 %

34

eprints.utm.my

Internet Source

<1 %

35

garuda.kemdikbud.go.id

Internet Source

<1 %

36

www.frontiersin.org

Internet Source

<1 %

37

www.jeeng.net

Internet Source

<1 %

38

"A New Generation Material Graphene: Applications in Water Technology", Springer Science and Business Media LLC, 2019

Publication

<1 %

39

Mengtian Sun, Yang Wang, Xiaowu Wang, Qiong Liu, Ming Li, Yury M. Shulga, Zhi Li. "In-Situ Synthesis of Layered Double Hydroxide/Silica Aerogel Composite and Its Thermal Safety Characteristics", Gels, 2022

Publication

<1 %

Exclude quotes Off

Exclude matches Off

Exclude bibliography On